

FLAMMABILITY TEST REPORT

Report No.: 380886A/06 Date Received : 10/11/06 Date Tested: 14/11/06 Date Issued: 14/11/06

Company Name & Address: GALA TENT LIMITED
 UNIT 1 PARK SPRINGS
 SPRING VALE ROAD
 GRIMETHORPE
 BARNSELY
 SOUTH YORKSHIRE
 S72 7BQ

Contact Name: JASON MACE

Sample Details

Order / Reference no.: FC2007
 Invoice number: Not stated
 Quality: Not stated
 Colour(s) : White
 Supplier: Not stated
 End use: Marquee fabric
 Fabric type: Woven
 Sample description: 1 piece of white coloured coated woven fabric

Test Method	Pre Treatment	Performance requirement	Result
BS 5438:1989 Test Method 2B	Watersoaked as clause 3 of BS 5651: 1989 then line dried	BS 7837: 1996	PASS



.....

KRISTIAN LEE (Flammability Technician)	STEVEN OWEN (Flammability Technician)	SIMON CHEE (Area Leader)	ANDREW WHITE (Quality Manager)
--	---	------------------------------------	--

FLAMMABILITY TEST REPORT

Test Specification

Test method	Test method 2B of BS 5438: 1989 as required by BS 7837: 1996
Criterion of ignition:	40mm high Butane gas flame
Ignition type:	Bottom edge (Raw)
Flame application time:	10 seconds
Sample size:	200 x 160mm

Pre-treatment / Durability procedure

Watersoaked as clause 3 of BS 5651: 1989 then line dried

Conditioning

Prior to testing:	At least 24 hours in an atmosphere having a temperature of 20±2°C. and a relative humidity of 65±5%
At time of testing:	Temperature between 15°C & 30°C. Relative humidity between 35% & 75%. Air movement less than 0.2m/s.

Test Results

“ The test results were obtained using the specified test conditions and do not necessarily represent the behavior of the test material under other conditions of test or use.”

Specimen No. /Direction	Afterflame (Secs)	Afterglow (Secs)	Flaming debris	Flame to edge	Hole to edge	Maximum hole extent (mm)
1. Warp ↑	0.0	0.0	No	No	No	50
2. Warp ↓	0.0	0.0	No	No	No	59
3. Warp ↑	0.0	0.0	No	No	No	57
4. Weft →	0.0	0.0	No	No	No	72
5. Weft ←	0.0	0.0	No	No	No	76
6. Weft →	0.0	0.0	No	No	No	70

Conclusions

The sample tested meets the requirements of BS 7837: 1996. **PASS.**